

COIMEX INTERNATIONAL LTD
 PO BOX 204 302 Highbrook 2161
 3 Ra Ora Drive, East Tamaki 2013
 Auckland, New Zealand
 Tel: (09) 274 1348 Fax: (09) 274 1351
 Email: sales@coimex.co.nz



COIMEX INTERNATIONAL LTD • AUCKLAND

Fibertechs

GLASS SCRIM FABRIC with weave lock finish
PRODUCT SPECIFICATION

Style Number	03798
Finish/Designation	FG180169

	Unit	Tolerance Specification		
Material- and Design data				
Yarn	tex			DIN EN 12654
warp		EC11-204		
weft		EC12-1200		
Fibre count	1/cm			DIN EN 1049
warp ends		6,0	± 5%	
weft picks		1,3	± 5%	
Fabric weave pattern		Leno		DIN ISO 9354
Edge weave pattern		Feathered Edge		
Area weight	g/m ²	285,0	± 5%	DIN EN 12127

Properties / finished fabric				
Area weight	g/m ²	340,0	± 5%	DIN EN 12127
Mesh size	mm x mm	6 x 5	± 10%	
Finish content	%	18 - 22		DIN ISO 1887
Starting tensile strength	N/5cm			DIN ISO 4606
warp		3300	± 10%	
weft		3600	± 10%	
Tensile strength 1)	N/5cm			DIN ISO 4606
warp			min.	
weft			min.	
Thickness (approx.)	mm	0,85		DIN ISO 4603/E

Other properties

1) Min. tensile strength after 28 days in Sodium Hydroxide (5%)