

Technical Data Sheet

Rockcote Max Render

Description:

It is a meshing render for use over a masonry substrate in conjunction with alkali resistant fibreglass mesh.

Typical Use:

Base Coat applied over a masonry substrate.

Expectation:

Max Render will cure to form a strong crack resistant background which will accept a levelling coat.

Limitations:

Do not apply less than 5mm per coat. Must be used in conjunction with 150gsm Alkali resistant fibreglass mesh. Cannot be applied on Polystyrene or Fibre Cement Sheet.

Technical Data:

Mix ratio: 20kg plaster requires approx. 4L of water
Coverage: Base Coat 5mm thick approx. 2.5 - 3m²
Substrates: Masonry
Abrasive strength: Excellent
Vapour Permeability: No vapour barrier formed.

Surface Preparation:

Ensure surface is clean, sound, dry and free from dust, dirt, grease, mould and lichen. Painted surfaces should have a slurry coat applied. Glazed bricks should be scabbled and slurry coated.

Application:

Plaster is applied with a steel trowel or broad-knife. Apply with firm pressure lay in mesh and trowel well to embed mesh (for base coat only). Apply plaster only when the temperature is between 5°C and 30°C and will be in that range for the 24 hours period following application.

Curing:

Max Render should be protected from hot drying winds and direct sunlight for the first 16 hours.
Protect newly applied plaster from rain and water run off for the first 24 hours.

Clean up:

Wash equipment and spills as soon as possible with water.

Environmental and Safety

Ensure washing water does not enter waterways. Wet waste can be soaked into land or disposed of in trade waste. The powder is an irritant and paper dust masks are advised when handling. The wet compound is Alkaline and prolonged skin contact should be avoided. Wear rubber gloves, dust mask and safety glasses when handling product.

Material Safety Data Sheets are available on request.